

AITIOU

A2806C

◎ Amorphous Toroidal Core(Used Common-Mode Choke)

◎ Mechanical Properties:

| Bare Core Dimensions (mm) | | | Finished Core Dimensions (mm) | | | Case Material & Color |
|---------------------------|--------------------|-------------------|-------------------------------|--------------------|-------------------|-----------------------|
| od _{±0.3} | id _{±0.3} | h _{±0.3} | OD _{±0.5} | ID _{±0.5} | H _{±0.5} | |
| 28.00 | 18.0 | 10.0 | 29.8 | 16.60 | 12.4 | PBT or NY66, White |

◎ Typical Parameters and Magnetic Properties:

| Lm (mm) | Ac (mm ²) | Wa (mm ²) | WaAc (mm ⁴) | Vol (mm ³) | Bs@25°C (T) | μ _i 10KHz | A _L @10KHz (μ H) |
|------------|--------------------------|--------------------------|----------------------------|---------------------------|----------------|-------------------------|--------------------------------|
| 72.22 | 40.00 | 216.31 | 8652.58 | 3611.00 | 1.10 | 60000 | 40.0 Min |


◎ Core Finished Material:

Insulating Covers:UL94V-0 or equivalent

◎ Temperature Range:

Storage temperature-20 ~ +50°C Ambient Temperature

Operating Temperature -40 ~ +120°C Case Surface Temperature



| | | | | | |
|------|------|-------|--------|-------|------|
| WIRE | 0.5¢ | TURNS | 1.0 Ts | TEMP. | 25°C |
|------|------|-------|--------|-------|------|

TEST INSTRUMENTS: ZENTECH 3302 LCZ

The inductance attenuation curve

